🔷 allas concorde USA

> The Trilogy collection mixes a refined selection of the most sought-after white marbles quarried from the most renowned sites in the world: Italy and Greece. Shades represent the common theme between these precious stones which have been carefully selected for their bright white color and gray veins that vary depending on the original material, giving each a unique appeal and enhancing its own identity. Thanks to the reputation and the look of the natural stone, marble-look surfaces can be matched with different types of interior styles, from the most classic and elegant to the modern ones.

COLORS



TRILOGY VOLAKAS ROYAL



TRILOGY CARRARA CLASSIC




TRILOGY CALACATTA

trilogy PRODUCT SHEET







MOSAICS & DECORS



TRILOGY VOLAKAS **ROYAL MOSAIC** 11^{3/4}"x11^{3/4}" - 30x30 cm (Mosaic 2"x2")

MOOD



TRILOGY CARRARA CLASSIC MOSAIC 11^{3/4}"x11^{3/4}" - 30x30 cm (Mosaic 2"x2")



TRILOGY CALACATTA MOSAIC 11^{3/4}"x11^{3/4}" - 30x30 cm (Mosaic 2"x2")





TRILOGY CARRARA CLASSIC CHEVRON MOSAIC 14^{1/8}"x 9^{7/8}" - 36x25 cm (Mosaic 7.1"x1.2")



TRILOGY CALACATTA CHEVRON MOSAIC 14^{1/8}"x 9^{7/8}" - 36x25 cm (Mosaic 7.1"x1.2")

* Chevron Mix Mosaic includes Carrara Classic & Reflex Night



(Mosaic 7.1"x1.2")

ROYAL CHEVRON

14^{1/8}"x 9^{7/8}" - 36x25 cm

MOSAIC

TRILOGY CHEVRON MIX MOSAIC* 14^{1/8}"x 9^{7/8}" - 36x25 cm (Mosaic 7.1"x1.2")



TRILOGY VOLAKAS ROYAL ARABESQUE MOSAIC 13"x12^{5/8}" - 33x32 cm (Mosaic 2.7"x4.1")



TRILOGY CARRARA CLASSIC ARABESQUE MOSAIC 13"x12^{5/8}" - 33x32 cm (Mosaic 2.7"x4.1")



TRILOGY CALACATTA ARABESQUE MOSAIC 13"x12^{5/8}" - 33x32 cm (Mosaic 2.7"x4.1")

COORDINATING TRIMS



Bullnose 3"x 24" - 7.2x60 cm



trilogy

🗇 atlas concorde USA

Finish

Matte

Matte

COLORED BODY PORCELAIN TILE



Compliant with standards ANSI A137.1-2012

FIELD TILES - Available in all colors

Commercial size (in)

12" x 24

24" x 48"

SIZE - THICKNESS

11 3/4" x 23 5/8" - 30 x 60 cm ¥9mm FINISH 23 5/8" x 47 1/4" - 60 x 120 cm

MATTE

Rectified Edge

Yes



MODERATE VARIATION

While the colors and/or texture present on a single piece of tile will be indicative of the colors and/or texture to be expected on the other tiles, the amount of colors and/or texture on each piece may vary significantly. It is recommended that the range be viewed before selection.

Nominal size (in)

11 3/4" x 23 5/8"

23 5/8" x 47 1/4"

MOSAICS AND COORDINATING TRIMS - Available in all colors

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Please refer to caliber chart for work sizes.	
Mosaic 2" x 2"	11 3/4" x 11 3/4"	9 mm	Matte	Close joints	
Chevron Mosaic 7.1" x 1.2"	14 1/8" x 9 7/8"	9 mm	Matte	are not recommended.	
Arabesque Mosaic 2.7" x 4.1"	13" x 12 5/8"	9 mm	Matte	(*): Cove Base thickness	
Bullnose 3" x 24"	2 7/8" x 23 5/8"	9 mm	Matte	is 7mm on flat part.	
Cove Base 6" x 12"	5 7/8" x 11 3/4"	8.5 mm (*)	Matte		

Thickness (mm)

9 mm

9 mm

PERFORMANCE & FEATURES

				Porcelain Tile Specification				
		DRODEDTY	ASTM TEST METHOD	Calibrated		Rectified		
		PROPERTY		Minimum	Maximum	Minimum	Maximum	
		Nominal Size	ASTM C499	-3.00%	3.00%	-3.00%	2.00%	Compliant
		Caliber Range (Variation from average facial dimension of sample)		-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
		Thickness ⁽¹⁾		N/A	Range: 0.40 in (1.02 mm)	N/A	Range: 0.40 in (1.02 mm)	Compliant
		Wedging	ASTM C502	-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
	t ⊥ t	Warpage Edge	ASTM C485	-0.75% or -0.09 in (-2.3 mm) (*)	0.75% or 0.09 in (2.3 mm) (*)	-0.40% or -0.05 in (-1.3 mm)(2) or -1.8 mm(3) (*)	0.40% or 0.05 in (1.3 mm)(2) or 1.8 mm(3) (*)	Compliant
		Warpage Diagonal		-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.40% or -0.07 in (-1.8 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	Compliant
				All Porcelain Tiles				
STRUCTURAL CHARACTERISTICS		Water Absorption	ASTM C373	≤ 0.5%				≤ 0.5%
BULK MECHANICAL CHARACTERISTICS	\downarrow	Breaking Strength	ASTM C648	Average ≥ 250 lbf. (1.11 kN) Individual ≥ 225 lbf. (1.00 kN)				\ge 350 lbf. avg
PHYSICAL PROPERTIES		Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)				≥ 100 psi
THERMAL AND IGROMETRIC CHARACTERISTICS		Resistance to Freeze/ Thaw Cycling	ASTM C1026	As Reported				Resistant
		Chemical Resistance	ASTM C650	As Reported			Unaffected	
CHARACTERISTICS		Stain Resistance	ASTM C1378	As Reported			Unaffected	
SAFETY CHARACTERISTICS		Dynamic coefficient of friction	DCOF	Requires a minimum value of 0.42 for commercial areas that are likely to be wet				> 0.42 Wet

(*) Whichever is less

(1) May not apply to textured surfaces or tiles with uneven back patterns.

(2) Whichever is less, for tiles up to 24"x24" (610 mm x 610 mm).
(3) Applies to tiles larger than 24"x24" (610 mm x 610 mm).

The Health Product Declaration[®] logo is a registered trademark of HPD Collaborative.

