









Imballi - Packing - Verpackung - Emballage - Embalaje
DIGITAL PORCELLANATO
TECHNOLOGY IMPASTO COLORATO
CONTEMPORARY

Formato Size Format Formato	Pezzi/Scatola Pieces/Box Stück/Karton Pieces/Boîte Piezas/Caja	Mq./Scatola Sq.m./Box Qm./Karton M ² /Boîte Mq./Caja	Kg./Scatola Kg./Box Kg./Karton Kg./Boîte Kg./Caja	Scatole/Pallet Boxes/Pallet Kartons/Palette Boîte/Palette Caja/Pallet	Mq./Pallet Sq.m./Pallet Qm./Palette M ² /Palette Mq./Pallet	Kg./Pallet Kg./Pallet Kg./Palette Kg./Palette Kg./Pallet	Spessore Thickness Stärke Epaisseurs Espesor
44,5x90 rett.	3	1,200	28,90	32	38,40	940	10,5 mm
30x60	6	1,080	23,90	40	43,20	971	10 mm
29,6x59,5 rett.	5	0,900	23,90	48	43,20	1.162	10 mm
22x90 rett.	6	1,188	28,60	36	42,77	1.045	10,5 mm
10x59,5 rett.	12	0,700	16,90	60	42,00	1.029	10 mm
29,6x29,6 mix rett.	4	-	-	-	-	-	-
31x29 mosaico liscia	4	-	-	-	-	-	-
9x60 battiscopa	12	-	-	-	-	-	-
9x59,5 battiscopa rett.	12	-	-	-	-	-	-

**Dati tecnici secondo norme - Technical data conform to
 Caractéristiques techniques d'après normes
 Technische Daten nach den Normen**
EN 14411 B I₁ GL
CONTEMPORARY

Caratteristiche tecniche Technical data Caractéristiques techniques Technische Daten	Norme Norms Normes Norm	Valori ascot Value ascot Valeur ascot Wert ascot	Caratteristiche tecniche Technical data Caractéristiques techniques Technische Daten	Norme Norms Normes Norm	Valori ascot Value ascot Valeur ascot Wert ascot
 Resistenza all'abrasione Abrasion resistance Resistance à l'abrasion Abrasionswiderstandigkeit	ISO 10545-7	PEI IV	 Resistenza attacco chimico Chemical resistance Résistance chimique Chemischee beständigkeit	ISO 10545-13	Resiste Resists Resiste Bestanding
 Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	ISO 10545-3	< 0,5 %	 Resistenza alle macchie Stain resistance Resistance aux taches Fleckenfestigkeit	ISO 10545-14	Totale Complete Totale Absolut
 Resistenza alla flessione Breaking modulus Résistance à la flexion Biegefestigkeit	ISO 10545-4	40÷55 N/mm²	 Resistenza al gelo Resistance to frost Résistance au gel Frostbeständigkeit	ISO 10545-12	Non gelive Frost proof Ingeleit Frostsicher
 Durezza Mohs Mohs hardness Dureté Mohs Haerte Mohs	UNI 101	7	 Scivolosità Slipperiness Degré de glissement Rutschhemmung	ANSI A137-1	> 0,42
 Scivolosità Slipperiness Degré de glissement Rutschhemmung	DIN 51130	R 10	 Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschhemmung	DIN 51097	B
 Scivolamento B.C.R.A. Slipperiness B.C.R.A. Degré de glissement B.C.R.A. Rutschhemmung B.C.R.A.	TORTUS	> 0,40	 Stonizzazione Shading Denuançage Spielfarbig		V2

